

## Aluminium Powder-Uncoated

### Product: AT (LR)

Characteristics	UOM	Test Method	Specification
<b>Sieve Analysis</b>		<b>ASTM B-214</b>	
+ 425 µm	%		5.0 max.
- 425 + 250 µm	%		30 – 55
- 250 + 125 µm	%		40 – 65
- 125 µm	%		10.0 max.
<b>Metallic Impurities</b>			
Iron	%	M/QA/SOP/028	0.35 max.
Silicon	%	M/QA/SOP/028	0.15 max.
Copper	%	M/QA/SOP/028	0.01 max.
Manganese	%	M/QA/SOP/028	0.01 max.
Magnesium	%	M/QA/SOP/028	0.01 max.
Zinc	%	M/QA/SOP/028	0.01 max.
Sodium	%	M/QA/SOP/028	0.01 max.
<b>Aluminium Content</b>	%	M/QA/SOP/049	99.50 min.
<b>Active Aluminium Content</b>	%	M/QA/SOP/016	98.50 min.

M/QA/SOP028 & 049 based on AAS and M/QA/SOP/016 based on IS 438

Made out of primary high pure Aluminium ingot of > 99.7 % purity, by air atomization, irregular in shape, used for the applications like Brake linings, Chemical reactions, Diamond-resin wheels, Explosives, Ferro alloys, Foundry fluxes, Mining explosives, Sintering, Thermit welding etc

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process .

## MEPCO