



# Technical Data Sheet

## GOLD BRONZE POWDER

### Rich Gold Dusting

Trade Mark: C1

Characteristics	UOM	*Test Method	Specification
<u>Sieve analysis:</u>			
Passing through sieve 150 µm	%	M/QA/SOP/003	95 min
Passing through sieve 45 µm	%	M/QA/SOP/003	80 min
Passing through sieve 25 µm	%	M/QA/SOP/003	40 min
Leafing Power	%	M/QA/SOP/019	20 min
Water covering Capacity	cm <sup>2</sup> /g	M/QA/SOP/020	2000 min

\*M/QA/SOP/003,M/QA/SOP/019 & M/QA/SOP/020 are based on ISO-1247

C1 Dusting -type, Gold Bronze flake metal powder (Leafing) based on a high pure copper alloy (Brass) of approx 70 % Copper and 30 % Zinc, in a dry ball milling process, Rich Gold in shade and corn flake in shape, for the applications like Decorative coatings, Dry flower coatings, Idol paintings, Litho Dustings, Master batches, Textile printings etc

*The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.*

## MEPCO

Thirumangalam,  
Madurai  
PIN: 625706  
Tamilnadu, India  
Phone: + 91 4549 280599  
Fax: +91 4549 281273

E-mail: info@mepco.co.in  
Web: www.mepco.co.in

Edition: 02.01.2023  
Page 1 of 1