

Technical Data Sheet

GOLD BRONZE POWDER

Rich Gold Brilliant Super Lac

Trade Mark: C33

| Characteristics | UOM | *Test Method | Specification |
|------------------------------|--------------------|--------------|---------------|
| Sieve analysis: | | | |
| Passing through sieve 150 µm | % | M/QA/SOP/003 | 99.9 min |
| Passing through sieve 45 µm | % | M/QA/SOP/003 | 99 min |
| Passing through sieve 25 µm | % | M/QA/SOP/003 | 96 min |
| Leafing Power | % | M/QA/SOP/019 | 50 min |
| Water covering Capacity | cm ² /g | M/QA/SOP/020 | 4250 min |

*M/QA/SOP/003,M/QA/SOP/019 & M/QA/SOP/020 are based on ISO-1247

C33 Brilliant Super Lac-type, Gold Bronze flake metal powder (Leafing) based on a high pure copper alloy (Brass) of approx 70 % Copper and 30 % Zinc, in a dry ball milling process,Rich Gold in shade and corn flake in shape, for the applications like Aerosol, Decorative coatings, Screen printing, Textile coatings etc

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

MEPCO

Thirumangalam, Madurai PIN: 625706 Tamilnadu,India Phone: + 91 4549 280599 Fax: +91 4549 281273 E-mail:info@mepco.co.in Web:www.mepco.co.in Edition: 02.01.2023 Page 1 of 1