

## FLITTER

## ALUMINIUM POWDER

Trade Mark: FF55

| Characteristics   | UOM    | Test Method                  | Specification    |
|---|--------|------------------------------|------------------|
| <u>Sieve analysis:</u><br>Residue on sieve 150 $\mu$ m<br>Residue on sieve 45 $\mu$ m | %<br>% | M/QA/SOP/003<br>M/QA/SOP/003 | 5 max<br>50 – 70 |
| Volatile Matter   | %      | M/QA/SOP/017                 | 1 max            |
| Leafing power   | %      | M/QA/SOP/018                 | Nil              |
| Matter soluble in organic solvent   | %      | M/QA/SOP/006                 | 1 – 4            |

\* M/QA/SOP/003, M/QA/SOP/017, M/QA/SOP/006 are based on ISO-1247.

FF 55 Flitter Non Leafing Aluminium Powder platelets in shape, for applications like Chrome finish decorative dustings and coatings, Plastic coatings, Plastic master batches, Powder coatings, Textile coatings etc

*The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.*

## MEPCO

Thirumangalam,  
Madurai  
PIN: 625706  
Tamilnadu, India  
Phone: + 91 4549 280599  
Fax: +91 4549 281273

E-mail: info@mepco.co.in  
Web: www.mepco.co.in

Edition: 02.01.2023  
Page 1 of 1