

## Magnalium Powder - Uncoated

### Product: Magnalium Powder 10 mesh-uncoated

Characteristics	UOM	Test Method	Specification
<b>Sieve Analysis</b>		<b>IS 17403</b>	
+ 1700 $\mu$ m	%		3.0 max.
- 1700 + 300 $\mu$ m	%		Balance.
- 300 $\mu$ m	%		10.0 max.
<b>Chemical Analysis</b>			
<b>Magnesium</b>	%	M/QA/SOP/028	45.0 min
<b>Aluminium</b>	%	M/QA/SOP/028	45.0 min.

M/QA/SOP028 based on AAS

Alloying of > 99.80 % high pure Magnesium ingot and > 99.70 % pure Aluminium Ingot as Raw Materials used for the manufacture of Magnalium Powder 10 mesh –uncoated, granular shaped powder, for the applications like Fireworks for making crackling sound and sparking sparks in sparklers, Ferro alloys, Foundry flux, Refractory bricks etc.

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process

## MEPCO