

Magnalium Powder - Uncoated

Product: Magnalium Powder 200 mesh-uncoated

Characteristics	UOM	Test Method	Specification
Sieve Analysis		IS 17403	
Retention on 75 µm	%		3.0 max.
Chemical Analysis			
Magnesium	%	M/QA/SOP/028	45.0 min
Aluminium	%	M/QA/SOP/028	45.0 min.

M/QA/SOP028 based on AAS

Alloying of > 99.80 % high pure Magnesium ingot and > 99.70 % pure Aluminium Ingot as Raw Materials used for the manufacture of Magnalium Powder 200 mesh –uncoated, granular shaped powder, for the applications like Fireworks for making white & color flickering in aerial shots /fountains/sparklers/twinklers, Ferro alloys, Foundry flux, Ordnance, Refractory bricks, Welding electrodes etc.

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process

MEPCO

Thirumangalam,
Madurai
PIN: 625706
Tamilnadu, India
Phone: + 91 4549 280599
Fax: +91 4549 281273

E-mail: info@mepco.co.in
Web: www.mepco.co.in

Edition: 02.01.2023
Page 1 of 1